



CHEMICAL INDUSTRIES INC.

TOLL FREE: 1-800-447-1437

FAX: 403-571-7977

TECHNICAL DATA SHEET

PRODUCT NAME:

Rubberized Crack Filler

CODE: 2104

Description:

Rubber Crack Filler is an emulsified asphalt containing rubber and selected fillers designed for sealing cracks in asphalt pavements. It is cold applied.

Uses:

Rubber Crack Filler is a sealant for traffic bearing joints up to 6mm (1/4") wide in Portland cement concrete and asphaltic pavements, concrete bridges and other structures.

Limitations:

Rubber Crack Filler should not be used unless temperature is at least 10 deg C (50 deg F). It should not be used if there is a threat of rain. Do Not Freeze.

Physical Properties:

Color:	Black
Solids:	58 %
Weight:	1.01 kg/l (8.4 lb/US gal)
Dry to Touch:	2-3 hours
Dry to Traffic:	24 hours

Preparatory Work:

Cracks should be routed, water blasted or air blown. Standing water should be air blown away or brushed away. Where cracks are very deep, it is best to pour in sand or a suitable type of backing leaving at least 1.5 cm (1/2 in) to be filled with crack sealer.

Application Directions:

Stir thoroughly before using. **Rubber Crack Filler** can be applied with a spouted pouring can or with a pump and wand applicator. If cracks are not completely full after drying, refill a second time. Sprinkle sand to prevent tracking. Sand is not required if there is not traffic until the material is dry. Clean up with water or Mineral spirits.

Storage and Handling:

Do not freeze. Store in closed containers.

Packaging:

4 litre spouted bottle, 20 litre spout lid pail, 205 litre drum.